

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 128 452 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
29.08.2001 Bulletin 2001/35

(51) Int Cl.⁷: **H01M 4/50, C01G 45/02**

(21) Application number: **01300718.2**

(22) Date of filing: **26.01.2001**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• **Sumida, Hiroshi**
Ageo-shi, Saitama (JP)
• **Enomoto, Kiyoteru**
Takehara-shi, Hiroshima (JP)
• **Sato, Masaki**
Takehara-shi, Hiroshima (JP)

(30) Priority: **25.02.2000 JP 2000048802**

(71) Applicant: **Mitsui Mining & Smelting Co., Ltd**
Tokyo (JP)


(74) Representative: **W.P. THOMPSON & CO.**
Eastcheap House
Central Approach
Letchworth, Hertfordshire SG6 3DS (GB)

(54) **Manganese dioxide for lithium primary battery and process for producing the same**

(57) Manganese dioxide for lithium primary batteries which is obtained by soda neutralization and heat treatment of electrolytic manganese dioxide and has a

sodium content of 0.05 to 0.2% by weight and a phosphorus content of 0.05 to 2.0% by weight. A process for producing the same is also disclosed.

Fig. 1



EP 1 128 452 A1

Description**BACKGROUND OF THE INVENTION**

Field of the Invention:

[0001] The present invention relates to manganese dioxide for lithium primary batteries and a process for producing the same. More particularly, it relates to an improvement in a cathode active material of a lithium primary battery comprising lithium or a lithium alloy as an anode active material.

Description of the Related Art:

[0002] Typical cathode active materials known for lithium primary batteries comprising lithium or a lithium alloy as an anode active material include manganese dioxide, carbon fluoride, etc., which have been put to practical use.

[0003] Manganese dioxide out of these cathode active materials has been used out of preference because of its inexpensiveness and abundance.

[0004] Where manganese dioxide is used as a cathode active material, it is a generally followed practice that electrolytic manganese dioxide is heat treated at 350 to 430°C as disclosed, e.g., in Japanese Patent Publication No. 4064/82.

[0005] The electrolytic manganese dioxide to be heat treated is one having been neutralized with ammonia. Electrolytic manganese dioxide itself is useful as a cathode material in manganese dry batteries and alkaline manganese dry batteries. Ammonia-neutralized manganese dioxide is for manganese dry batteries, and soda-neutralized manganese dioxide is for alkaline manganese dry batteries. Electrolytic manganese dioxide having been neutralized with soda and heat treated contains 0.3 to 0.5% by weight of sodium. If the sodium-containing manganese dioxide is applied to a lithium primary battery, the lithium primary battery has significantly reduced discharge performance because the residual sodium in manganese dioxide contaminates the anode lithium to interfere with the electrode reaction.

[0006] For the above reason, ammonia neutralization has been adopted because ammonia evaporates together with the water content during heat treatment. It has been pointed out, however, that ammonia neutralization is accompanied by the problem of irritating smell given off on ammonia evaporation which deteriorates the working environment. In addition, an existing plant having no step of ammonia neutralization could not be applied as such to preparation of manganese dioxide for lithium primary batteries.

[0007] Ammonia-neutralized manganese dioxide has another disadvantage that it undergoes marked reduction in BET specific surface area, which leads to deterioration of low-temperature characteristics or storage characteristics when applied to lithium primary batter-

ies.

SUMMARY OF THE INVENTION

[0008] The present invention has been made in the light of the above-described circumstances. As a result of extensive investigation, the present inventors have found that neutralization of electrolytic manganese dioxide using a sodium-containing neutralizing agent can be accomplished while controlling the sodium content within a given range.

[0009] The present invention has been completed based on this finding. The present invention provides manganese dioxide with a sodium content of 0.05 to 0.2% by weight for lithium primary batteries which is obtained by neutralization by means of a sodium-containing neutralizing agent and heat treatment of electrolytic manganese dioxide.

[0010] The present invention also provides a process for producing manganese dioxide with a sodium content of 0.05 to 0.2% by weight for lithium primary batteries comprising the steps of neutralizing electrolytic manganese dioxide preferably with an aqueous solution containing 2.0 to 5.0 g of sodium hydroxide, or a sodium content equivalent thereto, per kg of manganese dioxide and then heating the neutralized manganese dioxide.

[0011] The manganese dioxide for lithium primary batteries according to the present invention can bring about improvements in the working environment, can have reduced sodium dissolution, and can bring about improved low-temperature characteristics and storage characteristics of batteries. The process according to the present invention can provide such manganese dioxide on an industrial scale with satisfactory workability and ease.

BRIEF DESCRIPTION OF THE DRAWINGS

[0012] The present invention will be more particularly described with reference to the accompanying drawings, in which:

Fig. 1 is a graph of JIS-pH vs. Na content of manganese dioxide;

Fig. 2 is a graph of electrical conductivity vs. Na content of manganese dioxide;

Fig. 3 is a graph of dissolved Na vs. Na content of manganese dioxide; and

Fig. 4 is a graph of dissolved SO₄ vs. Na content of manganese dioxide.

DETAILED DESCRIPTION OF THE INVENTION

[0013] The manganese dioxide for lithium primary batteries according to the present invention is electrolytic manganese dioxide obtained by an electrolysis process. As stated above, electrolytic manganese dioxide has advantages of inexpensiveness and abun-

dance.

[0014] The electrolytic manganese dioxide of the present invention has a sodium content of 0.05 to 0.2% by weight. When used as a cathode active material of a lithium primary battery, electrolytic manganese dioxide having a sodium content exceeding 0.2% by weight has its sodium content displaced with lithium and precipitated to reduce the storage characteristics of the battery. Electrolytic manganese dioxide with a sodium content smaller than 0.05% by weight has residual acidity due to insufficient neutralization, causing reduction in storage characteristics of the battery.

[0015] The manganese dioxide of the invention preferably has an amount of sodium dissolution of 20 g/l or less. If the amount of sodium dissolution exceeds 20 g/l, sodium will be displaced with lithium to reduce the storage characteristics of the battery as mentioned above.

[0016] As compared with ammonia-neutralized manganese dioxide, the soda-neutralized manganese dioxide of the present invention is advantageous in that the reduction in BET specific surface area is small when heat treated. That is, when treated at 430°C for 4 hours, ammonia-neutralized manganese dioxide reduces its BET specific surface area from 50 m²/g to 20 m²/g, while the BET specific surface area of the soda-neutralized manganese dioxide (50 m²/g) is not reduced to less than 30 m²/g. This means that soda-neutralized manganese dioxide could be heat treated at higher temperatures than ammonia-neutralized manganese dioxide, with the resultant reduction in BET specific surface area being the same, to bring about improvements on low-temperature characteristics and storage characteristics of batteries.

[0017] The manganese dioxide according to the present invention can preferably be produced as follows. The starting manganese dioxide is obtained by electrolysis. For example, a manganese sulfate aqueous solution having a prescribed concentration is electrolyzed at a constant current density while warming by using a carbon plate as a cathode and a titanium plate as an anode to deposit electrolytic manganese dioxide on the anode. The deposited electrolytic manganese dioxide is peeled from the anode, ground, and neutralized. It is particularly preferred to use manganese dioxide having a phosphorus content of 0.05 to 2.0% by weight disclosed in Japanese Patent Publication No. 1698/94.

[0018] Neutralization is preferably carried out with a sodium hydroxide aqueous solution. The sodium content in the manganese dioxide may be controlled by using an aqueous solution containing 2.0 to 5.0 g of sodium hydroxide per kg of the manganese dioxide. The sodium hydroxide aqueous solution usually has a concentration of 100 to 150 g/l. The neutralizing agent which can be used is not limited to sodium hydroxide and includes sodium carbonate and sodium hydrogencarbonate having an equivalent sodium content.

[0019] The soda-neutralized electrolytic manganese dioxide is washed with water, dried, and then heat treat-

ed to obtain manganese dioxide for lithium primary batteries which contains 0.05 to 0.2% by weight of sodium.

[0020] The present invention will now be illustrated in greater detail with reference to Examples. The following Examples are presented as being exemplary of the present invention and should not be considered as limiting. Unless otherwise noted, all the percents are by weight.

EXAMPLES 1 AND 2 AND COMPARATIVE EXAMPLES 1 TO 3

[0021] Electrolytic manganese dioxide having a phosphorus content of 0.25% was neutralized by addition of a sodium hydroxide aqueous solution having the concentration shown in Table 1 below. The neutralized manganese dioxide was collected by filtration, washed with water, and dried. The manganese dioxide was then heated at 430°C for 4 hours. The sodium content of the resulting manganese dioxide is shown in Table 1.

[0022] For comparison, ammonia-neutralized manganese dioxide was prepared in a conventional manner.

[0023] A CR123A type battery was assembled with each of the resulting manganese dioxide species as a cathode active material, a solution of LiCF₃SO₃ in a 1:1 mixed solvent of propylene carbonate and 1,2-dimethoxyethane as an electrolytic solution, and a lithium electrode as an anode material.

[0024] The batteries were subjected to a discharge cycle test in which a 3-second discharge at 900 mA followed by a 27-second rest made one cycle, and the discharge characteristics of the batteries and the color change of the lithium anode are shown in Table 1.

[0025] The soda-neutralized manganese dioxide species of Examples 1 and 2 and Comparative Example 1 were further evaluated in terms of JIS-pH, electrical conductivity, Na dissolution, and SO₄ dissolution in accordance with the following method. The results obtained are shown in Table 1.

(1) JIS-pH

Measured in accordance with JIS K1467.

(2) Electrical conductivity

With the use of a supernatant liquid obtained from the mixture of 10 g of manganese dioxide and 200 mL of deionized water after stirring the mixture for 20 minutes, measurement was carried out with a commercially available portable conductivity meter,

(3) Na dissolution

Measured by ICP analysis.

(4) SO₄ dissolution

Measured by ICP analysis.

TABLE 1

	NaOH (g/kg-MnO ₂)	Na Content (%)	Discharge Cycle	Color Change of Li	Smell on Heat Treatment	Product Na Content (%)	JIS-pH	Conductivity (μ S/cm)	Na Dissolution (mg/l)	SO ₄ Dissolution (mg/l)
Example 1	3.0	0.1	101	no change	no smell	0.1	2.4	100	10	35
Example 2	5.0	0.2	100	no change	no smell	0.2	3.4	50	12	12
Comparative Example 1	10.0	0.5	54	observed	no smell	0.5	4.8	150	25	8
Comparative Example 2	-	0.01	46	no change	no smell	-	-	-	-	-
Comparative Example 3	NH ₃ - neutralized product	<0.01	100	no change	emitted	-	-	-	-	-

* The number of cycles of the NH₃-neutralized product was taken as a standard (100).

[0026] It can be seen from Table 1 that the products of Examples 1 and 2 are equal in performance to the conventional product of Comparative Example 3. The conventional soda-neutralized product of Comparative Example 1 and the non-neutralized product of Comparative Example 2 are inferior in cycle characteristics. The conventional ammonia-neutralized product of Comparative Example 3 emitted the smell of ammonia while heat treated. The soda-neutralized products of Examples 1 and 2 have a smaller amount of Na dissolution than the product of Comparative Example 1.

TEST EXAMPLE

[0027] Manganese dioxide species having a varied sodium content were prepared in the same manner as described above. The influence of the sodium content on JIS-pH, conductivity, Na dissolution, and SO₄ dissolution are shown in the plots in Figs. 1 through 4. It is recognized from these plots that the JIS-pH and Na dissolution reduce and the SO₄ dissolution increases with a decrease of the Na content.

Claims

1. Manganese dioxide for lithium primary batteries which is obtainable by neutralization by means of a sodium-containing neutralizing agent and heat treatment of electrolytic manganese dioxide and which has a sodium content of 0.05 to 0.2% by weight.
2. Manganese dioxide according to claim 1, which has a phosphorus content of 0.05 to 2.0% by weight.
3. A process for producing manganese dioxide with a sodium content of 0.05 to 0.2% by weight for lithium primary batteries comprising the steps of neutralizing electrolytic manganese dioxide by means of a sodium-containing neutralizing agent and then heating the neutralized manganese dioxide.
4. A process according to claim 3, wherein the neutralizing agent is an aqueous solution containing 2.0 to 5.0g of sodium hydroxide, or a sodium content equivalent thereto, per kg of manganese dioxide.
5. A process according to claim 3 or 4, wherein the neutralizing agent is an aqueous solution of one or more of sodium hydroxide, sodium carbonate and sodium hydrogencarbonate.
6. A process according to any of claims 3 to 5, wherein said electrolytic manganese dioxide has a phosphorus content of 0.05 to 2.0% by weight.
7. A lithium primary battery comprising the manga-

nese dioxide according to claim 1 or 2 as a cathode active material.

5

10

15

20

25

30

35

40

45

50

55

5

Fig. 1




Fig. 2




Fig. 3





Fig. 4





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 30 0718

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	PATENT ABSTRACTS OF JAPAN vol. 2000, no. 05, 14 September 2000 (2000-09-14) -& JP 2000 048817 A (MATSUSHITA ELECTRIC IND CO LTD; MITSUI MINING & SMELTING CO LTD), 18 February 2000 (2000-02-18) * abstract *	1,3-5	H01M4/50 C01G45/02
P, X	& EP 1 043 275 A (MITSUI MINING & SMELTING CO ; MATSUSHITA ELECTRIC IND CO LTD (JP)) 11 October 2000 (2000-10-11) * paragraphs '0006!', '0008!', '0013!', '0014!', '0019!', '0024!' * * table 1 *	1,3-5	
X	US 5 698 176 A (CAPPARELLA MARK ET AL) 16 December 1997 (1997-12-16) * column 1, line 4 - column 2, line 62 * * column 4, line 54 - line 57 * * example 1 * * claim 3 *	1,3-5,7	
X	PATENT ABSTRACTS OF JAPAN vol. 015, no. 258 (E-1084), 28 June 1991 (1991-06-28) -& JP 03 084858 A (TOSHIBA BATTERY CO LTD), 10 April 1991 (1991-04-10) * abstract *	1	TECHNICAL FIELDS SEARCHED (Int.Cl.7) H01M C01G
X	PATENT ABSTRACTS OF JAPAN vol. 015, no. 273 (E-1088), 11 July 1991 (1991-07-11) -& JP 03 093163 A (SANYO ELECTRIC CO LTD), 18 April 1991 (1991-04-18) * abstract *	1	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 19 April 2001	Examiner Métais, S
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 02.92 (P04001)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 30 0718

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	EP 0 373 791 A (MITSUI MINING & SMELTING CO) 20 June 1990 (1990-06-20) * page 2, line 30 - page 3, line 3 * * examples 4-7 * * table 1 * * claims 1,2 * -----	2,6,7	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 19 April 2001	Examiner Métais, S
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03 82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 30 0718

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

19-04-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 2000048817 A	18-02-2000	AU 4060799 A	21-02-2000
		CN 1273564 T	15-11-2000
		EP 1043275 A	11-10-2000
		WO 0006496 A	10-02-2000
US 5698176 A	16-12-1997	AU 5982596 A	30-12-1996
		BR 9608570 A	29-12-1998
		CA 2222516 A	19-12-1996
		CZ 9703858 A	15-07-1998
		EP 0842118 A	20-05-1998
		JP 11506721 T	15-06-1999
		NZ 309614 A	30-08-1999
		PL 323713 A	14-04-1998
		WO 9640588 A	19-12-1996
		US 5863675 A	26-01-1999
		ZA 9603652 A	20-11-1996
JP 03084858 7 A		NONE	
JP 03093163 7 A		NONE	
EP 0373791 A	20-06-1990	JP 1877535 C	07-10-1994
		JP 2155166 A	14-06-1990
		JP 6001698 B	05-01-1994
		AU 4567989 A	14-06-1990
		CA 2004744 A, C	07-06-1990
		DE 68914960 D	01-06-1994
		DE 68914960 T	11-08-1994
		US 5156933 A	20-10-1992

EPO FORM P449

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82